

Hempalin Primer 12050

Product characteristics

Description

Hempalin Primer 12050 is a quick-drying alkyd primer containing zinc phosphate.

Complies with EU Directive 2004/42/EC, subcategory i.

Recommended use

Hempalin Primer 12050 is a general purpose primer for Hempalin systems for protection of steel in mild to medium atmospheric corrosive environments.

Service temperature:

- Maximum, dry exposure only: 120°C [248°F].

Certificates / Approvals

- EC-type examined as a low flame spread material when used as part of a predefined paint system. Please refer to "Declaration of Conformity" on hempel.com for further details.

Features

- For newbuild and maintenance.
- Fast drying.
- Easy to apply with brush and roller.

Product safety

Flash point 38°C [100°F]

VOC content

Legislation	Value	5% thinning, by volume	Limit value, phase II (2010) ^a
EU	404 g/L [3.37 lb/US gal]	427 g/L [3.56 lb/US gal]	500 g/L [4.17 lb/US gal]
US (coatings)	404 g/L [3.37 lb/US gal]	-	
US (regulatory)	404 g/L [3.37 lb/US gal]		
China	404 g/L [3.37 lb/US gal]		

According to specific legislation, see details in the Explanatory Notes available at Hempel website, hempel.com or at your local Hempel website. VOC values may vary with shade, please consult the Safety Data Sheet, section 9. ^aEU Directive 2004/42/CE.

Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

Product data

Product code

12050

Standard shade* / code

Green 40760

Gloss

Flat

Volume solids

49 ± 2%

Specific gravity

1.3 kg/L [11 lb/US gal]

Hempalin Primer 12050

Reference dry film thickness

40 micron [1.6 mils]

Surface preparation

Cleanliness

- Remove oil, grease and other contaminants by suitable detergent cleaning.
- Remove salts, detergents and other contaminants by high pressure fresh water cleaning.

New build:

- Abrasive blasting to min. Sa 2 (ISO 8501-1) / SP 6 (SSPC).
- Remove dust, blast media and loose materials.
- All damage of shopprimer and contamination from storage and fabrication should be thoroughly mechanically/chemically cleaned prior to final painting.

Maintenance and Repair

- Remove dust, blast media and loose materials.
- Minor areas may be hand or power tool cleaned instead of abrasive blasting.
- Spot abrasive blasting to min. PSa 2 (ISO 8501-2) / SP 6 (SSPC).

Consult Hempel's separate Surface Preparation Guidelines for more details.

Application

Mixing ratio

This product contains heavy particles. Stir well before use.

Thinner

Hempel's Thinner 08230

Cleaner

Hempel's Thinner 08230

Application method

Tool	Thinning max vol.	Application parameters
Airless spray	5%	Nozzle pressure: 150 bar [2200 psi] Nozzle orifice: 0.018"
Air spray	10%	Not Applicable.
Brush	5%	Not Applicable.

If brush or roller application is used, more coats will be necessary to achieve the specified dry film thickness. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

Film thickness

Specification range	Low	High	Recommended
Dry film thickness	30 micron [1.2 mils]	50 micron [2.0 mils]	40 micron [1.6 mils]
Wet film thickness	60 micron [2.5 mils]	100 micron [4 mils]	80 micron [3 mils]
Theoretical spreading rate	16 m ² /L [650 sq ft/US gal]	10 m ² /L [410 sq ft/US gal]	12 m ² /L [490 sq ft/US gal]

For best performance, avoid excessive film thickness. Product may be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate, drying and curing time and overcoating interval.

Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

Application remarks

- Stir well before use.

Hempalin Primer 12050

Drying and overcoating

Product compatibility

- Previous coat: None.
- Subsequent coat: According to Hempel's Specification. Recommended products are: Hempalin

Drying time

Surface temperature		10°C [50°F]	20°C [68°F]	30°C [86°F]	40°C [104°F]
Touch dry	min	55	30	20	15
Surface dry	min	90	45	35	20
Hard dry	hours	3	1½	1	¾
Through dry	hours	10	4½	3	2

Determined for dry film thickness 40 micron [1.6 mils] at standard conditions, see Hempel's Explanatory Notes for details.

Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name		10°C [50°F]	20°C [68°F]	30°C [86°F]	40°C [104°F]
Atmospheric medium					
Hempalin Primer 12050	Min	16 h	8 h	6 h	4 h
	Max	5½ d	72 h	54 h	36 h
Hempalin Enamel 52140	Min	16 h	8 h	6 h	4 h
	Max	5½ d	72 h	54 h	36 h

Overcoating times are indicative for products of the same generic chemistry. Consult Hempel's specification for more information.

Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.

Overcoating details

- If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
- The surface must be dry and clean prior to application.

Other remarks

- Hempel's Specification supersedes any recommendations given in the Product Data Sheets.

Storage

Shelf life

Ambient temperature	25°C [77°F]
Product	60 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Storage at elevated temperatures may reduce shelf life. For advice, please consult Hempel.

Storage conditions

- Product must be stored according to local legislation, at maximum 40°C [104°F], without direct sunlight and protected from rain and snow.

Carbon Footprint

Dry film thickness	1 µm	1 mil
GWP (Global Warming Potential)	6.8 g CO ₂ e/m ²	0.036 lb CO ₂ e/ft ²

The carbon footprint is for 1 square meter / square foot of surface area with a dry film thickness of 1 micron / mil.

The scope includes raw materials, in-bound transport to the Hempel factory, Hempel manufacturing processes, and any Volatile Organic Compounds emitted during and after the application of the product.

It is calculated based on the standard shade defined in this PDS. Values may vary with shade.

Hempalin Primer 12050

Additional documents

Additional information is available at the Hempel website <https://www.hempel.com/service-and-support/technical-guidelines> or at your local Hempel website:

- Explanatory Notes for Product Data Sheet.
- Application methods.
- Surface Preparation.
- Application Instruction for this product.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.